

PRODUCT INFORMATION

CHEMOLINE 55 CN

PRODUCT DESCRIPTION

CHEMOLINE 55 CN is an already vulcanised black soft rubber lining based on Natural rubber (NR) with excellent properties against wear and which is equipped with an easy to bond, reactive bonding layer. **CHEMOLINE 55 CN** can be loaded directly without further vulcanisation.

FIELDS OF APPLICATION

Due to its excellent wear properties **CHEMOLINE 55 CN** is used mainly for on-site rubber linings of steel and concrete components which are exposed to abrasive conditions and chemical loads. The field of applications are mainly mineral processing plants and fertilizer industry. Some typical examples of applications are rubber lining of the storage tanks, filter vessels and agitated tanks.

FEATURES

- Excellent resistance against wear
- Good chemical resistance
- Application onto steel and concrete components
- Can be exposed to the operation conditions right after the application
- On site rubber lining

CHEMICAL RESISTANCE

Information on the chemical request is available on request.

SUBSTRATE

Substrates are components made of non-ferrous metals, cast iron, ferrite or austenitic steel, concrete, screed or plaster. Components to be rubber lined shall be designed and manufactured in accordance with EN 14879-1. For components made of concrete, screed or plaster DIN 1045 must also be observed.

SURFACE PRE-TREATMENT C-STEEL

Surfaces to be rubber lined must be dry and free of contaminants. All contaminants, including non-visible detectable contaminants, must be removed in accordance with DIN Fachbericht #28 and EN ISO 8502.

Ferrite steel surfaces shall be abrasive blasted to "Near White Metal" in accordance with EN ISO 12944-4. A standard preparation degree of SA 2½ (SSPC SP-10; NACE #2) as specified in EN ISO 8501-1 and a "medium (G)" roughness degree as specified in EN ISO 8503-1 must be achieved. A minimum surface profile of Rz ≥ 50 microns is required. To prevent flash rust, the primer must be applied immediately after the blasting and cleaning of the substrate or the component must be air conditioned.

CONCRETE

Appropriate action shall be taken to prepare the concrete surfaces; dry and free of dust and free of contaminants such as oil or grease. The concrete shall have minimum tensile strength of 1.5 N/mm² and minimum compressive strength of 25 N/mm². The residual moisture content must not exceed 4%. Generally the concrete surface must be smoothed prior to rubber lining application by applying an Epoxy resin

based mortar coat. This coat should be conductive to enable a subsequent spark test (**REMAFIX C**).

ENVIRONMENTAL CONDITIONS

Throughout the rubber lining process, the temperatures of the substrate and rubber lining materials shall be maintained within the range specified by TIP TOP. All surfaces shall be maintained at a temperature at least 3K above the dew point in order to prevent condensation.

ADHESIVE SYSTEM

CHEMOLINE 55 CN is bonded on steel or concrete components by using the primer system **PRIMER PR 304** in combination with the adhesive system **CEMENT BC 3004** with 4% **HARDENER E 40**.

APPLICATION METHOD UND CONSUMPTION

During the application of the product, the application instruction must always be observed.

Coat	Product	Application Method	Coverage [g/m ²]
1. Coat steel	PRIMER PR 304	Roll / Spray	ca. 150
2. Coat steel	CEMENT BC 3004	Roll	ca. 200
3. Coat steel	CEMENT BC 3004	Brush	ca. 200
1. Coat rubber	CEMENT BC 3004	Brush	ca. 200

If **PRIMER PR 304** is applied by airless spray, **PRIMER PR 304** must be diluted with **SOLVENT CE** in a mixing ratio of 1:1

CLEANING

Clean all equipment with **SOLVENT CF-CE** immediately after use.

VULCANISATION

Due to the already completed vulcanisation at the workshop, no further thermal treatment is longer necessary.

SPARK TEST

The spark test (holiday test) of new rubber linings is carried out according EN 14879-4 by using a high voltage tester. For carrying out the spark test, only the high voltage testers of Elmed model Isotest II RT or P as well as the test pistols of Wegener model WEG 20 or 22 or 100 are allowed.

CHEMOLINE 55 CN	Test Voltage [kV/mm]	Max. Test Voltage [kV]
vulcanised	5.0	20.0

SAFETY MEASURES

The material safety data sheets of the individual components, the safety instructions on the packing (label) as well as the legal requirements for handling hazardous materials must be observed.

CHEMOLINE 55 CN

PACKING UNITS

The products are supplied in the following standard package sizes:

Product	Size	Article No.
CEMENT BC 3004	4.5 kg	525 4095
CEMENT BC 3004	9 kg	525 4143
CEMENT BC 3004	18 kg	525 4130
HARDENER E 40	30 g	525 1067
PRIMER PR 304	0.75 kg	525 4112
PRIMER PR 304	10 kg	525 4150
SOLVENT CF-CE	10 l	595 9163

PACKAGING OF RUBBER SHEETS

The rubber sheets are wrapped with PE-separating sheets on cardboard cores, and packed freely suspend in stable, stackable card boxes, to avoid pressure points.

CHEMOLINE 55 CN is manufactured by extrusion in the following standard sizes:

Size (Tolerances according EN 14879-4)	Product-No.
3 mm x 1100 mm x 10000 mm	528 9895
4 mm x 1100 mm x 10000 mm	528 9905
5 mm x 1100 mm x 10000 mm	528 9912
6 mm x 1100 mm x 10000 mm	528 9929

STORAGE

The products must be stored in a cool and dry place, away from direct sunlight. The rubber sheets must be stored free of pressure, best in the original packaging. The rubber sheets may not receive any pressure points. At the specified storage temperatures a shelf life of the products is given of at least for the following periods:

Product	Temperature	Shelf Life
CEMENT BC 3004	5 - 25°C	24 Months
CHEMOLINE 55 CN	≤ +30°C	24 Months
PRIMER PR 304	5 - 25°C	12 Months
SOLVENT CF-CE	5 - 25°C	60 Months

If the storage time is exceeded, the materials must be tested before use. Higher storage and transport temperatures will reduce the shelf life. The containers must be kept tightly closed. Liquid products must be stored frost-proof. In addition, the DIN 7716 must be observed.

Technical Data	Standard	Unit	Value
Polymer Base	ISO 1629	-	NR
Abrasion	ISO 4649 (ASTM D5963)	mm ³	≤ 100
Density	EN ISO 1183-1	g/cm ³	1.11 ± 0.02
Hardness Shore A	ISO 7619-1 (ASTM D2240)	-	55 ± 5**
Max. Surface Pressure	-	N/mm ²	2
Elongation at Break	DIN 53504 (ASTM D412)	%	≥ 520***
Tensile Strength	DIN 53504 (ASTM D412)	N/mm ²	≥ 22***
Impact Resilience	DIN 53512 (ASTM D1054)	%	≥ 63
Peel Strength to Steel	ISO 813	N/mm	≥ 4
Max. Continuous Operating Temperature	-	°C	+60
Temperature Range	-	°C	-40 up to +60

** Autoclave vulcanisation *** 4 mm rubber

Note: The indicated temperatures are dependent on the present load and may vary

Information given in the fact sheet above corresponds to the current knowledge available to us regarding our products at the time of its drafting and is intended as a guideline for informational purposes. However, because of the multiple possibilities regarding possible applications, processing and on site conditions, any information given in the fact sheet above is not legally binding, in particular, without being limited to, such information shall not be interpreted as a warranty of merchantability or of fitness for a particular purpose. Customer therefore is advised to conduct its own testing or make an inquiry with our technical department before ordering. We reserve the right to change the product at any time, in particular, without being limited to, minor changes because of advancements in technology. If by way of exception, the information given in the fact sheet above is incorporated by reference into any contract concluded with us under German Law, such information, shall only be interpreted as determining the specific requirements of the contractual products as set out in § 434 BGB (German Civil Code) and shall not be interpreted as constituting a guarantee of condition.

TIP TOP Oberflächenschutz Elbe GmbH, Christian-Heibel-Strasse 51, D-56422 Wirges
Phone: +49 (0) 2602 949 50-0 / Fax: +49 (0) 2602 949 50-11 / E-Mail: info@tiptop-elbe.de

TIP TOP Oberflächenschutz Elbe GmbH	CHEMOLINE 55 CN	Revision 1.00 - 13.03.2015
Replaces all former editions	PRODUCT INFORMATION	Page: 2/2